

CAS N°: 1309-48-4

Properties

MgO (Magnesium Oxide)	_____	83,00 min % - 88,95% máx
Mg content	_____	50,05 min % - 53,63% máx
CaO (Calcium Oxide)	_____	3,50 min % - 4,50% máx
SiO ₂ (Silicom Oxide)	_____	4,50 min % - 6,20% máx
Fe ₂ O ₃ (Iron Oxide)	_____	0,40 min % - 1,00% máx
Al ₂ O ₃ (Aluminum Oxide)	_____	0,15 min % - 0,30% máx
LOI (Loss of ignition)	_____	2.50 min % - 5,00% máx

Physical Properties:

500μ	_____	0,00 max %
300μ	_____	10,00 max %
(-)300μ	_____	90,00 min %

* Transcripción literal de la ficha técnica del proveedor